

## PRODUCT DOCUMENTATION

## REVIMAR

### 1. DESCRIPTION

One-component and acrylic rubber based waterproof agent.

### 2. USES AND APPLICATIONS

It can be used as a waterproofing system for terraces, rooftops or any other surface that may be moved afterwards.

### 3. CHARACTERISTICS

- Total waterproofing system.
- Perfect adhesion to the surface.
- Accessible
- Anti-slipping
- High flexibility for a better absorption of shocks and climatic dilatation and contraction.
- Excellent resistance against wearing, impacts and slipping.
- Variety of colours: red, grey, green.
- Ecological.

### 4. TECHNICAL DATA

Characteristics	Norm
Firm material at 105°C, 82% of its mass	UNE 48.087
Completely dried at 23°C, relative humidity of 50%, in 24h	UNE 48.086
Resistance to impacts, no perforations after an impact	UNE 53.358
Resistance to slipping, 0.9%	UNE 53.358
Resistance to abrasion, humidity, loss of mass, 0.03gr/500	UNE 53.358

### 5. INSTRUCTIONS FOR USE

Before using, remove from package. Once the surface is prepared, pour a first layer of CRYLTOP and spread it to cover all the area. After 24h, apply the first layer of REVIMAR A-884, and wait 24h before applying the second layer to allow greater thickness. Before applying the second layer, make sure that the first layer is completely dry. While the first layer is still wet, a 20cm width woven glassfibre may be applied on the expansion joints, all along the joints.

If you want to apply the woven glassfibre all over the surface to waterproof, it must be applied on the first layer while it is still wet, then apply pressure with the steamroller to keep it impregnated to the product.

The glass fibre's flaps must be 15 cm long and placed in such a way that may ease the evacuation of water.

If the screed touches the Wall, the product and the glassfibre must be risen up 25cm.

## 6. PERFORMANCE/CONSUMPTION

To guarantee a perfect waterproofing, it is recommended to apply 2 kg/m<sup>2</sup> in different layers.

## 7. PACKAGING

Hermetic metallic containers, coated with an internal epoxy protection of 1, 5 and 30kg.

## 8. SAFETY AND HYGIENE

REVIMAR must be stored in hermetically closed containers, protected from frost. The brushes and tools used for its application must be immediately washed and rinsed with water.

## 9. OBSERVATIONS

The surface must be dry and clean. We recommend you the RAPIDOL or RURAID cleaning products. For better results on smooth, not porous surfaces, it is advisable to apply a layer of our adhesive prime coat ADERAN to provoke a better chemical anchoring. The irregular surfaces must be levelled to prevent stagnation of water.

This information and, especially, the recommendations about the application and final use of the products is given in good faith. It is based on the current knowledge and experience of RUDERIL IBERICA on the products when they are stored in convenient conditions, manipulated and applied in normal situation, before the end of its usable life.

In practice, the possible differences between the materials, supports and real conditions and surfaces to treat are such that one cannot deduce from the information provided in this document, written recommendations, or pieces of advice, any guarantee in terms of commercialization or suitability for particular purposes, nor any obligation beyond any legal relations that could exist.

The property rights of third parties must be respected.

All requests are accepted in accordance to the terms of our current General conditions of sales and delivery.